

FLUORESCENT MATERIAL

Patent Number: JP56057877
Publication date: 1981-05-20
Inventor(s): TAKEDA TAKESHI; others: 01
Applicant(s): MATSUSHITA ELECTRIC IND CO LTD
Requested Patent: ☐ JP56057877
Application Number: JP19790134555 19791017
Priority Number(s):
IPC Classification: C09K11/475
EC Classification:
Equivalents: JP1372462C, JP61036798B

Abstract

PURPOSE: To provide a novel fluorescent material consisting of lanthanum thiogallate doped with cerium, emitting green light by electron rays or ultraviolet rays excitation, having excellent light-emitting characteristics, and suitable for the fluorescent material of a flying spot tube, an index tube, etc.

CONSTITUTION: For example, La_2S_3 is mixed with equimolar amount of Ga_2S_3 , and a cerium compound is added to the mixture as an activating agent. The composition is calcined in a sulfurating atmosphere such as H_2S at 800-950 deg.C to obtain the objective fluorescent material. The starting materials are not restricted to the above sulfides, and the oxides such as La_2S_3 , Ga_2O_3 , CeO_2 , etc. may be used. The light-emitting characteristics of the fluorescent material can be further improved by using a slightly excess Ga_2S_3 in the mixing of La_2S_3 and Ga_2S_3 .

Data supplied from the esp@cenet database - 12

Display index tube - used in flat panel display.

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 56-057877

(43)Date of publication of application : 20.05.1981

(51)Int.CI. C09K 11/475

// H01J 29/20

(21)Application number : 54-134555

(71)Applicant : MATSUSHITA ELECTRIC IND CO LTD

(22)Date of filing : 17.10.1979

(72)Inventor : TAKEDA TAKESHI

MACHIDA IKUHIKO

(54) FLUORESCENT MATERIAL

(57)Abstract:

PURPOSE: To provide a novel fluorescent material consisting of lanthanum thiogallate doped with cerium, emitting green light by electron rays or ultraviolet rays excitation, having excellent light-emitting characteristics, and suitable for the fluorescent material of a flying spot tube, an index tube, etc.

CONSTITUTION: For example, La_2S_3 is mixed with equimolar amount of Ga_2S_3 , and a cerium compound is added to the mixture as an activating agent. The composition is calcined in a sulfurating atmosphere such as H_2S at $800\text{--}950^\circ\text{C}$ to obtain the objective fluorescent material. The starting materials are not restricted to the above sulfides, and the oxides such as La_2S_3 , Ga_2O_3 , CeO_2 , etc. may be used. The light-emitting characteristics of the fluorescent material can be further improved by using a slightly excess Ga_2S_3 in the mixing of La_2S_3 and Ga_2S_3 .